

Flowable polyester molding compositions

Abstract

- 5 Thermoplastic molding compositions comprising
- A) from 10 to 99.99% by weight of at least one thermoplastic polyester,
  - B) from 0.01 to 50% by weight of a hyperbranched polycarbonate having an OH number of from 1 to 600 mg KOH/g of polycarbonate (to DIN 53240, Part 2),
  - 10 C) from 0 to 60% by weight of other additives,

where the total of the percentages by weight of components A) to C) is 100%.